

Protan SK

Technical data

The numbers will vary because of different character patterns.

Base:	Paper	80g/m ²
Total Product Weight:		300g/m ²
Steam Revision	EN 1931:2000	8.6 g/m ² 24h
Strekstyrke	EN 12311-2	150-200 N/5cm
Fracture Extension	EN 12311-2	2-4%
Tear Strength	EN 12310-2	20 N
Shiny		2-5
Wearability	Taber Wear Abraser CS10/500g/500rpm	2.10 g
Light fastness	Xenotest	> 300 h
Fire	NT Fire	004 OK

February 2009